



PRODUCT SPECIFICATIONS

NH Nonhardening HEAT TRANSFER COMPOUND

APPLICATION

NH nonhardening heat transfer compound is used where thermal expansion and contraction could break the bond of a hardened compound. Typically installed between plate-type heating coils or with systems that require periodic disassembly, NH remains pliable indefinitely, allowing the compound to expand and contract to meet the changing requirements for the application.

Thermon's heat transfer compounds provide an efficient thermal connection between the external heating source and the process equipment. Thermon's NH compound improves the overall heat transfer coefficient by a minimum factor of three. By eliminating the air voids that would ordinarily exist, heat is directed into the surface area primarily through conduction rather than convection and radiation.



SPECIFICATIONS/RATINGS

Container sizes

NH-QT	1-quart (0.946-liter) cans
NH-100	1-gallon (3.79-liter) cans
NH-500	5-gallon (18.93-liter) cans
Maximum exposure temperature	375°F (190°C)
Minimum exposure temperature	-320°F (-196°C)
Minimum installation temperature	
Ambient temperature	32°F (0°C)
Product temperature	> 200°F (93°C)
Heat transfer coefficient, U _i	heater to tank wall 20-40 Btu/hr•°F•ft ² (114-227 w/m ² •°C)
Electrical resistivity	320 ohms/inch (126 ohms/cm)
Shelf life	indefinite
Water-soluble	no

DESCRIPTION

Nonhardening heat transfer compound is available in one-quart cans as well as one and five-gallon cans. NH is nonsoluble in most liquids. Compound remains pliable and requires no curing procedures.

BENEFITS

- Provides excellent heat transfer for systems having significant differential expansion
- Requires no curing
- Non-soluble in water
- No surface preparation required
- Remains pliable for easy disassembly
- Free design assistance

THERMON The Heat Tracing Specialists®



Corporate Headquarters: 100 Thermon Dr • PO Box 609 San Marcos, • TX 78667-0609 • Phone: 512-396-5801 • 1-800-820-4328
For the Thermon office nearest you visit us at . . . www.thermon.com